

Technical Data Sheet

Atelier24 Strong 956 Fliese

Needle-punched fibre web tile



Article number(s):	021 024 044 063 085
	088 089 141 180 181

Pictograms / Quality seal / Certificates



DoP number: TEPSTR956

05 | 2021

Information subject to technical modification and error. All previous data sheets are superseded by this issue.

W. & L. Jordan GmbH | Horst-Dieter-Jordan-Straße 7-10 | D-34134 Kassel | info@joka.de | www.joka.de
INKU Jordan GmbH & Co. KG | IZ-NÖ Süd | Straße 3 | A-2355 Wiener Neudorf | info@inku.at | www.inku.at



Technical Data Sheet

Atelier24 Strong 956 Fliese

Material / structure

Type of production	Needle-punched fibre web
Wear layer	70 % polyamide/ 20 % polyester/ 10 % polypropylene
Backing design	Bitumen
Wear layer charge weight (g/m ²) approx.	500
Total weight (g/m ²) approx.	4.200
Total height (mm) approx.	6,5
Dimensions (cm) approx.	50 x 50
Packaging unit (m ²)	5,00
Repeat (L x W in cm)	Repeat free

Product characteristics

Hard-wearing value	33 high - commercial
Comfort value	LC1 - simple
Improvement in impact sound (dB) approx.	18
Degree of sound absorption (α_w)	0.15
Lightfastness	≥ 5
Suitable for dissipative laying	yes
Resistance to earth (Ω)	$\leq 1 \times 10^8$
Thermal resistance (m ² xK/W) approx.	0,08
Fire behaviour	B _{fl} -s1
Anti-static	yes
Slip resistance	DS
Suitable for chair castors	yes

Tolerances

Deviation in height	Nominal value + 15 %, - 10 %
Deviation in length	Nominal length \pm 1.0 %
Deviation in width	Nominal width \pm 1.0 %
Deviation in number of tufts	Nominal value + 10 %, - 7.5%
Deviation in pile weight	Mean value + 13 %, - 10 %
Deviation in total weight	Nominal value \pm 15 %

Dimensions and tolerance values in accordance with the standards DIN EN 14159 and EN 1307. Dimensional characteristics and permitted dimensional deviations, which have been determined in the factory, have been given in accordance with the standard.